

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
23 October 2003 (23.10.2003)

PCT

(10) International Publication Number
WO 03/086260 A1

(51) International Patent Classification⁷: **A61F 13/58**

(21) International Application Number: PCT/US03/05689

(22) International Filing Date: 24 February 2003 (24.02.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/121,458 12 April 2002 (12.04.2002) US

(71) Applicant: **3M INNOVATIVE PROPERTIES COMPANY** [US/US]; 3M Center, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(72) Inventors: **JACKSON, Byron M.**,; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). **WOOD, Leigh E.**,; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). **STOREY, Roderick L.**,; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). **METZ, James V.**,; Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(74) Agents: **BOND, William J.**, et al.; Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT (utility model), AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (utility model), DE, DK (utility model), DK, DM, DZ, EC, EE (utility model), EE, ES, FI (utility model), FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ,

LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK (utility model), SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- *as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)*
- *as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations*

[Continued on next page]

(54) Title: ELASTIC CLOSURE TAB



(57) Abstract: There is provided a nonwoven elastic laminate closure tab of the invention comprising adjacent first and second nonwoven closure elements each having a first face and a second face and a coextruded film elastic attached to each closure element first face. The first face of each closure element has a first area coated with a pressure sensitive adhesive and a second area adjacent the first area free of pressure-sensitive adhesive at terminal ends of the nonwoven closure elements. The coextruded film elastic has two first regions each having at least one inelastic zone and a second region between the two first regions having at least one elastic zone. The two opposing first regions are attached to the two pressure-sensitive adhesive areas of the two closure elements respectively such that the second adhesive free areas of the two adjacent closure elements are in face to face contact with at least a portion of the coextruded elastic film elastic second region. The layers are all of a thickness such that the thickness variation across the closure tab is less than 50%.



WO 03/086260 A1



Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

ELASTIC CLOSURE TAB

Background of the Invention

The present invention relates to a novel elasticated fastener laminate for use in disposable absorbent articles and the like.

Disposable absorbent articles often use tab fasteners that are provided with elastic to allow for adjustment in the fit and a more secure and snug fit. For example, U.S. Patent No. 3,800,796 (Jacob) teaches disposable diapers with elastic tabs wherein the tabs have an elastic segment between two inelastic segments. One of the inelastic segments is used to attach the tab to the diaper and the other inelastic segment has a PSA to allow the tab to close the diaper. The tab can be made such that the entire tab is formed of an elastic material and the two terminal segments are rendered inelastic, for example by laminating an inelastic material to the end segments. In Jacob, the elastic would be exposed to the adhesive if a tab precursor laminate were directly wound into a roll. This is problematic in that elastics generally can become permanently bonded to or contaminated by adhesives. This construction does not protect the elastic from direct contact with the adhesive. Further, the tabs vary in thickness which would inhibit the formation of a stable roll of the precursor tab fasteners laminate.

U.S. Patent No. 4,522,853 (Szonn) also discloses an elastic tab adhesive closure for disposable diapers. The tabs disclosed in this patent have an intermediate (middle) elastic piece and adhesive coated end portions. The tab disclosed and claimed is complex and includes multiple additional elements. Szonn again does not protect its elastic from direct contact with adhesive layers. The constructions disclosed in Szonn are complicated and have multiple different layers that would result in considerable variation in the tab thickness making stable roll formation difficult.

U.S. Patent No. 4,643,729 (Laplanche) also discloses a complex elastic fastener for disposable diapers that comprises three parts. These are, a first lateral side part (inelastic, for attaching to the diaper during manufacturing), a second lateral side part (inelastic, containing PSA for closing the diaper), and an elastic central part. The two lateral parts are parts of a single piece composed of a support band provided with a transverse pre-cut line, which are separated at the time of use (along the pre-cut line). The two lateral parts are bonded to the central elastic part with adhesive bands and the lateral parts also have

adhesive on the face opposite the elastic part for bonding to the diaper (one end for manufacturers bond the other end for closing the diaper in use). The elastic tabs taught in Laplanche again would not protect its elastic material from adhesive contact when wound in a roll.

5 U.S. Patent No. 4,778,701 (Pape) discloses a roll of laminated strips from which separate elastic closure tabs can be cut. This is a pre-laminated elastic tab closure with a central elastic portion and inelastic end portions, one for attaching to the diaper during manufacturing and one for the consumer to use to close the diaper. The elastic in Pape is also not protected from exposure to the adhesive without an extra piece of protective
10 material. The thickness of this material would also vary significantly over the width of the tab which is undesirable.

U.S. Patent. No. 4,795,456 (Borgers) discloses an extensible tab for disposable diapers that is stabilized (inextensible) until the user deploys the tab for diapering. This inextensibility of the elastic central segment is achieved by the tab construction including
15 a non-extensible web (e.g. a release tape or liner) that bridges the inextensible end segments (as does the elastic segment) until the tab is opened for use. In Borgers, the elastic is again not protected from the adhesive. Also, the construction requires multiple adhesive layers and film layers such that it would be costly and difficult to manufacture.

U.S. Patent No. 4,834,820 (Kondo) discloses an elastic diaper closure tab
20 containing an elastic sheet and an inelastic retaining sheet which is directly bonded to the elastic sheet in the terminal end regions and the inelastic sheet has a cut-off groove in the center portion. When using the diaper the consumer manually rips apart the retaining sheet along the cut-off groove, whereupon the center of the elastic sheet is made flexible (elastic) as the retaining sheet no longer bridges the elastic sheet between the areas where
25 the retaining sheet and the elastic sheet are bonded. The tab further has adhesive on the underside of the elastic sheet to anchor the tab to the side of the diaper (manufacturers bond) and to be used for closing the diaper. The structures (elastic tabs) taught in Kondo again require multiple layers of adhesive and fails to protect the elastic from direct contact with the adhesive layers if wound into a roll.

30 U.S. Patent No. 5,057,097 (Gesp) discloses elastic diaper tape tabs wherein there is adhesive on the end segments and a central segment free of adhesive, and wherein the tape backing is a multilayer elastic film (e.g. a co-extruded elastic with inelastic skin layers).

In Gesp, the elastic is protected from direct exposure to the adhesive layers but the terminal portions are not necessarily inelastic as the entire tab is generally elastic which could result in the tab failing during use. Also, the elastic is always exposed prior to use.

5 HEI 4[1992]-17059 (Sho 59[1984]-67022 /Kokei No. Sho 60-215803, Hida)
discloses a tab for disposable diapers having non-extensible end regions and an extensible sheet that connects the end regions and in which at least one part of the overlap ping area of the end members and the extensible sheet are non-bonded. Again, the elastic in this construction is not protected from contact with the adhesive if wound into a roll form and a complicated multiple step construction process is required.

10 There is a need for a tab construction utilizing an elastic central region where the terminal ends are inelastic, which tab is easy to manufacture and provide in a stable roll form and where the elastic is simultaneous securely attached to the inelastic region and protected from direct contact with adhesive if wound into a roll while providing excellent aesthetic features.

15

Summary of the Invention

The nonwoven elastic laminate closure tab of the invention comprises adjacent first and second nonwoven closure elements each having a first face and a second face and a coextruded film elastic attached to each closure element first face. The first face of each
20 closure element has a first area coated with a pressure sensitive adhesive and a second area adjacent the first area free of pressure-sensitive adhesive at terminal ends of the nonwoven closure elements. The coextruded film elastic has two first regions each having at least one inelastic zone and a second region between the two first regions having at least one elastic zone. The two opposing first regions are attached to the two pressure-sensitive
25 adhesive areas of the two closure elements respectively such that the second adhesive free areas of the two adjacent closure elements are in face to face contact with at least a portion of the coextruded elastic film elastic second region. The layers are all of a thickness such that the thickness variation across the closure tab is less than 50%.

30

Description of the Drawings

FIGURE 1 is a perspective view of a disposable absorbent article using the invention elastic tab closure.

FIGURE 2 is a side view of the invention tab closure.

FIGURE 3 is a side perspective of the invention tab closure.

FIGURE 4 is a side view of the invention tab closure in an extended condition.

FIGURE 5 is a perspective of the invention tab closure in an extended condition.

5

Detailed Description of the Preferred Embodiment

Fig. 1 shows the invention elastic closure tab 4 in use on a disposable absorbent article 1. The elastic closure tab is extended and attached at two opposing side regions of the disposable absorbent article 1.

10 As shown in Figs. 2-3, the nonwoven elastic laminate closure tab 4 of the invention comprises adjacent first 20 and second 21 nonwoven closure elements each having a first face (31, 33) and a second face (32, 34) and a coextruded film elastic 10 attached to each closure element first face (31, 33). The first face (31, 32) of each closure element has a first area (23, 25) coated with a pressure sensitive adhesive (14, 19) and a second area (24, 15 26) adjacent the first area (23, 25) free of pressure-sensitive adhesive at terminal ends (36, 37) of the nonwoven closure elements (20, 21). The coextruded film elastic 10 has two first regions (11, 12) each having at least one inelastic zone and a second region 13 between the two first regions having at least one elastic zone. The two opposing first regions (11 and 12) are attached to the two pressure-sensitive adhesive coated areas (23, 20 25) of the two closure elements (20, 21) respectively such that the second adhesive free areas (24, 26) of the two adjacent closure elements (20, 21) are in face to face contact with at least a portion of the coextruded elastic film 10 elastic second region 13. The pressure-sensitive adhesive layer (14, 19) is provided with a first region (16, 17), attached to the coextruded elastic film 10 first region (11, 12), and a second adhesive region (15, 18) free 25 for attachment to other elements. The layers are all of a thickness such that the thickness variation across the closure tab 4 is preferably less than about 50 percent, and most preferably less than about 40%.

The two adjacent closure element second adhesive free zones (24, 26) form the opposing terminal ends (36, 37) of the closure elements (20, 21) and are preferably in an 30 abutting face to face relation such that they cover substantially all the elastic film second region 13 as shown in Figs. 2 and 3. In this way, the elastic film second region 13 is covered prior to use to protect it from adhesive contamination while also minimizing

thickness variation across the closure tab 4 in the central region of the closure tab. There are also functional and aesthetic advantages. The elastic can be colored differently than the closure elements or provided with designs so as to provide distinct visual contrast. When the user extends the tab as shown in Figs. 4 and 5, by a distance 30, the previous covered elastic 13 is then clearly exposed. This provides a clear visual indication of the extent to which the elastic is stretched which is also a direct indication of the force being applied by the elastic. When two opposing tabs are used, the level of force could then be easily adjusted so that each tab is extended to the same degree. Generally, one can easily see when the elastic is being used and adjust the degree of stretch as appropriate.

The closure element terminal ends (36, 37) can either be separably attached or not attached as appropriate. If separably attached, such as by a serrated cut line, they should be easily separated with a minimum level of force. In any event, generally, the adjacent closure elements terminal ends (36, 37) should be less than 5 mm apart, preferably less than 3 mm apart and most preferably in a directly abutting relation.

A unique advantage of the invention construction is that the closure elements and elastic members are relatively thin and coextensive, however the elastic is generally substantially thinner than the closure element. Generally, the closure elements (20, 21) have a thickness of from 0.05 mm to 1.0 mm; preferably 0.1 mm to 0.5 mm. Generally, the film elastic 10 has a thickness of 0.03 mm to 0.5 mm; preferably 0.05 mm to 0.2 mm. Further, the film elastic 10 generally has a thickness of 20 to 60 percent of the thickness of the closure elements, preferably 20 to 50 percent.

The closure elements (20, 21) are preferably a laminate of a nonwoven and a film layer. The nonwoven provides softness while the film layer provides a barrier for the adhesive and/or dimensional stability. The nonwoven preferably is a spunbond nonwoven, having a basis weight from 20 gsm to 50 gsm, where the film layer is extrusion laminated to the spunbond nonwoven. The film layer can have a thickness of from 0.03 mm to 0.5 mm and is preferably adjacent the pressure-sensitive adhesive layer. The film layer can also be separately provided and adhesive laminated, sonic bonded or otherwise conventionally attached to the nonwoven layer. The pressure-sensitive adhesive layers are provided on the closure elements to both attach the film elastic to the closure elements (the first adhesive region 16, 17) and further to attach the closure elements to the disposable garment, or other article, on which it may be used or to other elements (the second

adhesive regions 15, 18). Preferably one and most preferably both closure elements have an area beyond the elastic film that has exposed second pressure-sensitive adhesive regions (15, 18) that can be used to attach the closure element or alternatively could be used to attach other elements such as mechanical fastener elements. The second exposed pressure-sensitive adhesive region (15, 18) generally is at least 200 mm², preferably at least 300 mm². The first pressure-sensitive adhesive region is generally at least 5 mm wide, preferably at least 10 mm wide.

The elastic film first regions (11, 12) generally have at least one zone that is inelastic to provide for secure adhesion to the closure elements (20, 21). This inelastic zone extends generally at least 0.5 mm, preferably at least 1 mm to 10 mm or more and would in a preferred embodiment would extend over the entire area attached to the first adhesive region. This provides for secure adhesion of the elastic film to the first adhesive regions (16, 17) without excessive use of the elastic material. The second elastic region 13 of the coextruded film elastic generally is from 10 to 30 mm, preferably from 15 to 25 mm for most uses in a disposable absorbent article. The second elastic region would have at least one or more elastic zones. The size of the elastic region selected of course depends on the size of the article being used with the tab and the exact nature of the article, its intended adjustability and the elastic forces required. The elastic region could be formed of at least one elastic zone, which could extend at least 0.5 mm, preferably at least 1 to 10 mm or more. The elastic zones, if not continuous, would be separated by inelastic zones. The use of inelastic zones in the elastic region would be useful in adjusting the elastic properties of the elastic region.

The overall length 40 of the closure element 13 also can vary greatly depending on the desired end use. Generally, the closure elements will be 40 to 100 mm, preferably 50 to 80 mm. The width 41 of the closure elements depends on the desired use and the width can be made to vary as is known in the art for differing functional attributes.

The coextruded elastic film 10 is preferably an elastomeric laminate comprising at least one elastomeric core layer and at least one relatively nonelastomeric outer layer. When selected regions of the skin layer are stretched beyond its elastic limit and relaxed, the surface of the film becomes microstructured and the elastomeric core in this area is formed into an elastic region.

The elastomer forming the elastomeric layer can broadly include any material which is capable of being formed into a thin film layer and exhibits elastomeric properties at ambient conditions. Elastomeric means that the material will substantially resume its original shape after being stretched. Further, preferably, the elastomer will sustain only small permanent set following deformation and relaxation which set is preferably less than 20 percent and more preferably less than 10 percent of the original length at moderate elongation. Generally, any elastomer is acceptable which is capable of being stretched to a degree that causes relatively consistent permanent deformation in a relatively inelastic skin layer. This can be as low as 50% elongation. Preferably, however, the elastomer is capable of undergoing up to 300 to 1200% elongation at room temperature, and most preferably up to 600 to 800% elongation at room temperature. The elastomer can be both pure elastomers and blends with an elastomeric phase or content that will still exhibit substantial elastomeric properties at room temperature.

Preferred elastomers include block copolymers which are elastomeric such as those known to those skilled in the art as A-B or A-B-A block copolymers. These block copolymers are described, for example, in U.S. Patent Nos. 3,265,765; 3,562,356; 3,700,633; 4,116,917 and 4,156,673. Styrene/isoprene, butadiene or ethylene-butylene/styrene (SIS, SBS or SEBS) block copolymers are particularly useful. Other useful elastomeric compositions can include elastomeric polyurethanes, ethylene copolymers such as ethylene vinyl acetates, ethylene/propylene copolymer elastomers or ethylene/propylene/diene terpolymer elastomers. Blends of these elastomers with each other or with modifying non-elastomers are also contemplated. For example, up to 50 weight percent, but preferably less than 30 weight percent, of polymers can be added as stiffening aids such as polyvinylstyrenes, polystyrenes such as poly(alpha-methyl)styrene, polyesters, epoxies, polyolefins, e.g., polyethylene or certain ethylene vinyl acetates, preferably those of higher molecular weight, or coumarone-indene resin. The ability to use these types of elastomers and blends provides the invention laminate with significant flexibility.

Viscosity reducing polymers and plasticizers can also be blended with the elastomers such as low molecular weight polyethylene and polypropylene polymers and copolymers, or tackifying resins such as Wingtack™, aliphatic hydrocarbon tackifiers available from Goodyear Chemical Company. Tackifiers can also be used to increase the

adhesiveness of an elastomeric layer to a skin layer. Examples of tackifiers include aliphatic or aromatic hydrocarbon liquid tackifiers, polyterpene resin tackifiers, and hydrogenated tackifying resins. Aliphatic hydrocarbon resins are preferred.

5 The relatively inelastic skin layer is preferably formed of any semi-crystalline or amorphous polymer that is less elastic than the core layer(s) and will undergo permanent deformation at the stretch percentage that the elastomeric laminate will undergo. Therefore, slightly elastic compounds, such as some olefinic elastomers, e.g. ethylene-propylene elastomers or ethylene-propylene-diene terpolymer elastomers or ethylenic copolymers, e.g., ethylene vinyl acetate, can be used as skin layers, either alone or in
10 blends. However, the skin layer is generally a polyolefin such as polyethylene, polypropylene, polybutylene or a polyethylene-polypropylene copolymer, but may also be wholly or partly polyamide such as nylon, polyester such as polyethylene terephthalate, polyvinylidene fluoride, polyacrylate such as poly(methyl methacrylate) and the like, and blends thereof. The skin layer material can be influenced by the type of elastomer
15 selected. If the elastomeric layer is in direct contact with the skin layer the skin layer should have sufficient adhesion to the elastomeric core layer such that it will not readily delaminate.

Additives useful in the skin layer include, but are not limited to, mineral oil . extenders, antistatic agents, pigments, dyes, antiblocking agents, provided in amounts less
20 than about 15%, starch and metal salts for degradability and stabilizers such as those described for the elastomeric core layer.

Other layers may be added between the core layer and the outer layers, such as tie layers to improve the bonding of the layers. Tie layers can be formed of, or compounded with maleic anhydride modified elastomers, ethyl vinyl acetates and olefins, polyacrylic
25 imides, butyl acrylates, peroxides such as peroxypolymers, e.g., peroxyolefins, silanes, e.g., epoxysilanes, reactive polystyrenes, chlorinated polyethylene, acrylic acid modified polyolefins and ethyl vinyl acetates with acetate and anhydride functional groups and the like, which can also be used in blends or as compatibilizers in one or more of the skin or core layers. Tie layers are particularly useful when the bonding force between the skin
30 and core is low. This is often the case with polyethylene skin as its low surface tension resists adhesion. However, any added layers must not significantly affect the microstructuring of the skin layers.

To provide for adjacent elastic and inelastic zones it is possible to either vary the skin layer or elastic layer in these regions or zones so that only certain areas are capable of being or becoming elastic. In an extreme case, the elastic core layer can be absent from a region or substantially thicker in a region to cause that region or zone to form an inelastic area such as described in U.S. Patent Nos. 5,057,097 (Gesp) or 5,773,374 (Wood et al.).
Alternatively, the elastic or skin layers can be treated in zones to weaken or strengthen them to provide elastic or inelastic zones, respectively. For example, zones or regions can be controlled to have lower overall modulus values that will preferentially yield before adjacent, in the direction of an orienting stress, higher modulus regions. This modulus control can be accomplished by a variety of methods that can involve the prelaminate formation stages, the formation stage, or post formation treatment of a particular laminate or laminate intermediate. Similarly, localization of stress, applied to the whole laminate, can result in preferential elongation in areas containing these localized stress regions. This stress control can also be effected by a variety of methods in any of a multitude of stages in the formation of the laminate. These strengthening or weakening treatments can include post formation annealing, selective crosslinking or selective plasticization, localized corona treatment, mechanical ablation, scoring, cutting out laminate material or indentation or the like, specific elastic zones can also be formed by controlled localized stretching as disclosed in U.S. Patent No. 5,344,691 (Hanschen).

After forming a zone activatable elastic laminate, the laminate is stretched past the elastic limit of the skin layer(s) exclusively or preferably in the lower modulus or preferred stress regions, which deform. The zone activated laminate then is recovered instantaneously, with time or by the application of heat. For heat activated recovery the inherent temperature of heat activation is determined by the materials used to form the elastic layer of the laminate in the first instance. However, for any particular laminate the activation temperature can be adjusted by varying the skin/core ratio of the laminate, adjusting the percent stretch or the overall laminate thickness. The activation temperature used for a heat shrink laminate is generally at least 80°F (26.7°C).

Activation will generally be accomplished by stretching the laminate in a direction substantially transverse to a primary extent of the film having spaced zones or regions of differing modulus or stress characteristics. At least one inelastic zone will be in the first region (11, 12) of the film attached to the closure element. At least one elastic zone will

be in the second region 13 unattached to the closure elements. Preferably inelastic zones will form at least 10 percent of first regions (11, 12), preferably at least 50 percent and in a preferred embodiment 100 percent. Preferably elastic zones will form at least 50 percent of the second region 13, preferably at least 80 percent and in a preferred embodiment 100 percent.

Test Methods

Shear Adhesion

A shear adhesion test was used to demonstrate the improvement in bond strength resulting from the adhesive bonding of a closure element nonwoven tape to an annealed elastic film. The shear adhesion was measured by determining the length of time it took for a 40 mm x 40 mm sample of nonwoven tape to shear off of an elastic film test substrate under a 0.5 kilogram load. A 40 mm x 65 mm piece of the elastic film substrate (cut such that the 65 mm dimension was in the cross-direction of the web) was laminated on both sides to a 90 mm x 50 mm piece of reinforcing tape (KN-1759, available from 3M Company) by folding over the reinforcing tape to sandwich the elastic film in order to enhance the stiffness of the substrate. A 25 mm section of the 65 mm length was left unreinforced. A 40 mm x 40 mm piece of nonwoven fastening tape (described below) was laminated to the unreinforced end of the elastic film by rolling it down onto the elastic film using four passes of a 5 kg hard rubber roller. The overlap region between the nonwoven tape and the elastic film was 12 mm x 40 mm. The nonlaminated end of the nonwoven tape was reinforced with a 90 mm x 50 mm piece of reinforcing tape (KN-1759, available from 3M Company) by folding over and stapling the reinforcing tape to sandwich the nonwoven tape. A small loop was left in the fold region of the reinforcing tape such that a brass hook could be slid into it. A 0.5 kilogram weight was hung from one end of the brass hook, generating a shear load in the overlap region at a 180° angle. The laminated elastic film and nonwoven tape were hung vertically in a 38°C oven. The time that it took in minutes for the bond in the overlap region to fail and the weight to drop was recorded in Table 1 below as a measure of the shear adhesion. Reported values are averages of 4 tests.

Laminates of the elastic film to the nonwoven tape were also prepared as above but were additionally heat bonded in the overlap region using a Sentinel Brand Heat Press

Model 808 set at 93°C for approximately 1 second at a pressure of 4.9 kg/cm² ("Heated Lamination") followed by shear testing.

Nonwoven Tape

5 The nonwoven tape was produced with a backing consisting of a 50 gram/m² polypropylene spunbond nonwoven web extrusion laminated to a 28 gram/m² polypropylene/polyethylene blended film. A 38 gram/m² pressure sensitive adhesive consisting of 50% Kraton 1119 (Kraton Polymers, Inc.) and 50% Wingtack Plus (Goodyear Chemical) was hot melt coated onto the film side of the backing. A solvent
10 based silicone polyurea was used as a release coating on the nonwoven side of the backing.

Examples & Comparatives

Comparative C1

15 A three layer coextruded elastic film was prepared as described in U.S. Patent 5,468,428 Example 1 except the two outer layers were made with 5E57 polypropylene (Dow Chemical) and the core elastomeric layer was made with a blend of 70% Kraton 1114 SIS block copolymer (Kraton Polymers) and 30% 678C polystyrene (Dow
20 Chemical). The thickness of each of the outer layers was 9 microns and the thickness of the core layer was 53 microns. The film was stretched in the cross-direction of approximately 6:1 to overstretch the outer layers and allowed to recover, thus rendering the entire film elastic. The film was elastic throughout its entire width and contained no inelastic annealed zones.

Example 1

An elastic film was prepared as in C1 above and subsequently stretched 6:1 in the cross-direction and then annealed with parallel longitudinal bands by passing the film over a patterned heated roll set at approximately 80°C. The inelastic annealed zones consisted of machine direction stripes 1.5 mm wide and 1 mm apart. The overlap region for the shear test described above contained approximately 50% annealed elastic film (inelastic zones) laminated to the nonwoven tape.

Example 2

An elastic film was prepared as in C1 above and subsequently stretched 6:1 in the cross-direction and then allowed to relax. The film was then stretched 4:1 and clamped into a fixture. A 5 cm wide inelastic zone was annealed in the middle of the clamped sample using a Sentinel Brand Heat Press equipped with a 5 cm wide sealing bar set at 121°C using a pressure of 4.9 kg/cm² for approximately 1 second. The overlap region for the shear test described above contained 100% annealed elastic film (inelastic zones) laminated to the nonwoven tape.

Table 1

Material	% Annealed Bond Area	Heated Lamination (Y/N)	Shear Failure Time (minutes)
C1	0	N	4
C1	0	Y	21
1	50	N	143
1	50	Y	380
2	100	N	>7100*
2	100	Y	>7100*

* test was discontinued at 7100 minutes

Table 1 shows that the bond strength between an elastic film and an adhesive tape is dramatically improved when the elastic film is annealed in the bonding region.

WHAT IS CLAIMED IS:

1. A nonwoven elastic laminate closure tab comprising adjacent first and second nonwoven closure elements each having a first face and a second face and a
5 coextruded film elastic attached to each closure element first face, wherein the first face of each closure element has a first area coated with a pressure sensitive adhesive and a second area adjacent the first area free of pressure-sensitive adhesive which second area includes terminal ends of the nonwoven closure elements, the coextruded film elastic has
10 two first region each having inelastic zones and a second region between the two first regions having elastic zones, wherein the two opposing first regions are attached to the two pressure-sensitive adhesive areas of the two closure elements respectively such that the second adhesive free areas of the two adjacent closure elements are in face to face contact with at least a portion of the coextruded elastic film elastic second region, wherein the thickness variation across the closure tab is less than 50 percent.
15
2. The nonwoven elastic laminate closure tab of claim 1 wherein the two adjacent closure element second adhesive free areas form the opposing terminal ends of the closure elements and are in a substantially abutting face to face relation such that the closure element second areas cover substantially all the elastic film elastic second region.
20
3. The nonwoven elastic laminate closure tab of claim 2 wherein the abutting closure element terminal elements are separably attached.
4. The nonwoven elastic laminate closure tab of claim 2 wherein the abutting
25 closure element terminal elements are not attached.
5. The nonwoven elastic laminate closure tab of claim 2 wherein the thickness variation across the closure tab is less than 40 percent.
6. The nonwoven elastic laminate closure tab of claim 1 wherein the closure
30 elements have a thickness of from 0.05 mm to 1.0 mm.

7. The nonwoven elastic laminate closure tab of claim 6 wherein the film elastic has a thickness of 0.03 mm to 0.5 mm.

5 8. The nonwoven elastic laminate closure tab of claim 7 wherein the film elastic has a thickness of 20 to 60 percent that of the closure elements.

9. The nonwoven elastic laminate closure tab of claim 6 wherein the closure elements are a laminate of a nonwoven and a film layer.

10 10. The nonwoven elastic laminate closure tab of claim 9 wherein the nonwoven is a spunbond nonwoven.

11. The nonwoven elastic laminate closure tab of claim 10 wherein the film layer is extrusion laminated to the spunbond nonwoven.

15

12. The nonwoven elastic laminate closure tab of claim 2 wherein the pressure-sensitive adhesive is exposed on at least one closure element.

13. The nonwoven elastic laminate closure tab of claim 12 wherein the pressure-sensitive adhesive is exposed on both closure elements.

20

14. The nonwoven elastic laminate closure tab of claim 12 wherein the exposed pressure-sensitive adhesive is at least 200 mm².

25 15. The nonwoven elastic laminate closure tab of claim 12 wherein the pressure-sensitive adhesive on at least one closure element has attached to it an attachment element.

16. The nonwoven elastic laminate closure tab of claim 15 wherein the attachment element is a hook element.

30

17. The nonwoven elastic laminate closure tab of claim 1 wherein the inelastic zone(s) in the first region are at least 0.5 mm wide.

5 18. The nonwoven elastic laminate closure tab of claim 1 wherein the total inelastic zone(s) in the first region are at least 10 percent of the first region.

19. The nonwoven elastic laminate closure tab of claim 1 wherein the total inelastic zone(s) in the first region are at least 50 percent of the first region.

10 20. The nonwoven elastic laminate closure tab of claim 1 wherein the total elastic zones in the second region are at least 50 percent of the second region.

1/3








Fig. 1

2/3

**Fig. 2****Fig. 3**

3/3



INTERNATIONAL SEARCH REPORT

Internatic Application No
PCT/Us 03/05689

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 A61F13/58

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 A61F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 1 133 967 A (3M INNOVATIVE PROPERTIES CO) 19 September 2001 (2001-09-19) column 11, line 27 -column 12, line 27; figures	1
A	WO 96 02218 A (MINNESOTA MINING & MFG) 1 February 1996 (1996-02-01) page 13, line 29-35; figures	1
A	EP 0 891 760 A (MINNESOTA MINING & MFG) 20 January 1999 (1999-01-20) abstract; figures	1
A	US 3 800 796 A (JACOB E) 2 April 1974 (1974-04-02) cited in the application abstract; figures	1
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

* & * document member of the same patent family

Date of the actual completion of the international search

28 May 2003

Date of mailing of the international search report

11/06/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Seabra, L

INTERNATIONAL SEARCH REPORT

Internatic application No
PCT/US 03/05689

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 643 729 A (LAPLANCHE PIERRE) 17 February 1987 (1987-02-17) cited in the application abstract; figures ---	1
A	EP 0 640 331 A (SCHICKEDANZ VER PAPIERWERK) 1 March 1995 (1995-03-01) abstract; figures -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No
PCT/US 03/05689

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1133967	A	19-09-2001	EP 1133967 A1	19-09-2001
			EP 1263375 A1	11-12-2002
			WO 0168025 A1	20-09-2001
			US 2003032359 A1	13-02-2003
WO 9602218	A	01-02-1996	AU 683395 B2	06-11-1997
			AU 2766295 A	16-02-1996
			BR 9508319 A	06-01-1998
			CA 2194276 A1	01-02-1996
			DE 69527981 D1	02-10-2002
			EP 0801552 A2	22-10-1997
			ES 2180644 T3	16-02-2003
			IL 114086 A	20-06-1999
			JP 10502842 T	17-03-1998
			WO 9602218 A2	01-02-1996
			US 5599601 A	04-02-1997
EP 0891760	A	20-01-1999	EP 0891760 A1	20-01-1999
			AU 8296598 A	10-02-1999
			DE 69808629 D1	14-11-2002
			EP 1256332 A2	13-11-2002
			EP 0996402 A1	03-05-2000
			ES 2181245 T3	16-02-2003
			JP 2001510074 T	31-07-2001
			WO 9903437 A1	28-01-1999
			US 2003008106 A1	09-01-2003
			US 6461715 B1	08-10-2002
US 3800796	A	02-04-1974	DE 2223359 A1	23-11-1972
			FR 2137855 A5	29-12-1972
			GB 1379689 A	08-01-1975
			IT 957814 B	20-10-1973
			NL 7206271 A	14-11-1972
			SE 368143 B	24-06-1974
US 4643729	A	17-02-1987	FR 2484798 A1	24-12-1981
			AR 227673 A1	30-11-1982
			AT 7448 T	15-06-1984
			BE 889261 A1	16-10-1981
			BR 8108654 A	11-05-1982
			CA 1168401 A1	05-06-1984
			DE 3163602 D1	20-06-1984
			DK 71182 A ,B,	18-02-1982
			EP 0054041 A1	23-06-1982
			ES 274140 U	01-01-1984
			ES 8401714 A1	16-03-1984
			FI 820561 A ,B,	19-02-1982
			WO 8103601 A1	24-12-1981
			GR 74569 A1	29-06-1984
			IE 51525 B1	07-01-1987
			IT 1144229 B	29-10-1986
			JP 1051561 B	06-11-1989
			JP 57500987 T	03-06-1982
			MX 170618 B	01-09-1993
			NO 820511 A ,B,	18-02-1982
			OA 6839 A	28-02-1983
			PT 73218 A ,B	01-07-1981

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US 03/05689

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0640331	A	01-03-1995	DE 4327589 A1 23-02-1995
			DE 59408837 D1 25-11-1999
			EP 0640331 A2 01-03-1995
			ES 2139693 T3 16-02-2000
